

STAR Technology

FORMULATING • INNOVATIVE • SOLUTIONS

633-02

EPOXY CASTING HIGH TEMPERATURE USE

DESCRIPTION

STAR Technology 633-02 is an aluminum filled, intermediate high temperature casting systems for applications up to 300°F. It requires a heat cure for applications above 150°F. 633-02 is formulated with special aluminum fillers for maximum heat transfer. When determining the maximum depth of a pour, factors to appraise include the configuration of the cast and the thermal conductance of the master. 633-02 is non-staining and may be cast up to 3 inches deep. Typical applications for 633-02 include high temperature autoclave tools, bonding fixtures, vacuum form molds, core boxes and patterns, and prototype injection molds.

BENEFITS

Accurate reproduction of detail
Long working life

Excellent machinability
No MDA or VCHD

TYPICAL PROPERTIES

		<u>TEST METHOD</u>	<u>VALUE</u>
Mix Ratio, Resin to Hardener	Parts by Weight		100:9.3
	Parts by Volume		100:15.79
Mixed Viscosity (centipoise)		ASTM D2393	22,000
Density (lbs./cu.ft.)		ASTM D1475	95
(lbs./gal.)			12.75
Pot Life at 75°F (minutes)		ASTM D2471	64
Color			Grey
Cure Schedule:	<i>24 hours @ 75°F + 2 hours @ 150°F + +1 hour @ 200°F + 1 hours @ 250°F + +1 hour @ 300°F + 2 hours @ 350°F</i>		
Shore Hardness (D)		ASTM D2240	87
Thermal Conductivity (Cal/hr cm°C)			70.7
Ultimate CTE (in/in/°C)		4.0x10 ⁻³	
Shrinkage (mm/mm)			nil
Compressive Ultimate Strength (psi)		ASTM D695	10000
Glass Transition Temperature (°F)		By DSC	360
Maximum Service Temperature (°F)			400
Tensile Strength			3240 psi
Flexural Strength			6280 psi
Flexural Modulus			926000
Coeff or exp. (in/in/°C)			3.2xE-5

To the best of our knowledge, the information contained herein is accurate. However, STAR TECHNOLOGY, Inc., does not assume any liability whatsoever for the accuracy or completeness of the information contained herein. Final determination of the suitability of any material is the sole responsibility of the user. The information contained herein is considered typical properties and is not intended to be used as specifications for our products. This information is offered solely to assist purchaser in selecting the appropriate products for purchaser's own testing. All materials may present unknown hazards and should be used with caution. Although certain hazards are described herein and in the material safety data sheet, we cannot guarantee that these are the only hazards that exist. Repeated and prolonged exposure to epoxy resins can cause sensitization or other allergic responses.

STAR Technology

FORMULATING • INNOVATIVE • SOLUTIONS

633-02**EPOXY CASTING HIGH TEMPERATURE USE****APPLICATION PROCEDURE**

Carefully weigh out appropriate amounts of resin and hardener into a clean container and mix until all streaks are gone. Scrape the sides and bottom frequently to ensure complete mixing. Pour the mixed material in the thinnest stream possible onto a single spot of the mold cavity. Allow the mixture to flow over the mold surface to help eliminate air entrapment.

NOTE: To obtain optimum service temperature follow the suggested curing schedule with thermocouple monitoring. Thermocouple monitoring equipment is recommended on all post cured tools. High temperature tools should be post cured prior to use. High temperature tools should be cured 50°F beyond anticipated use temperature.

CAUTION: Unmixed material from the sides or bottom of the container can cause soft spots or uncured areas in the completed tool. To prevent this, transfer the entire mixed contents to a second clean container and re-mix for a short time before using.

Additional Cure Schedule - If thermocouple monitoring equipment is not available then a longer step cure is a better choice, e.g.

2 hours @ 150°F + 2 hours @ 200°F +

2 hours @ 250°F + 2 hours @ 300°F +

2 hours @ 350°F

SAFETY PRECAUTIONS

For industrial use only. Keep away from children.

Refer to the Safety Data Sheets (SDS forms) pertaining to this product before using.

Avoid contact with skin or eyes. In the event of an eye splash or contact, immediately flush with cold water for 15 minutes and contact a physician. If skin contact occurs, wash with mild soap and water. The wearing of safety glasses with side shields and impervious gloves is recommended.

RESIN WARNING STATEMENT

Warning! Causes irritation. May cause allergic skin reaction. Avoid all contact with skin, eyes, and clothing. Wash thoroughly after handling.

HARDENER WARNING STATEMENT

Danger! Corrosive. Causes burns to eye and skin. May cause allergic skin and/or respiratory reaction or sensitization. Do not get in eyes, on skin or clothing. Keep container closed. Use with adequate ventilation. Wash thoroughly after handling.

To the best of our knowledge, the information contained herein is accurate. However, STAR TECHNOLOGY, Inc., does not assume any liability whatsoever for the accuracy or completeness of the information contained herein. Final determination of the suitability of any material is the sole responsibility of the user. The information contained herein is considered typical properties and is not intended to be used as specifications for our products. This information is offered solely to assist purchaser in selecting the appropriate products for purchaser's own testing. All materials may present unknown hazards and should be used with caution. Although certain hazards are described herein and in the material safety data sheet, we cannot guarantee that these are the only hazards that exist. Repeated and prolonged exposure to epoxy resins can cause sensitization or other allergic responses.