



FISil SI9100 Dielectric Gel

FEATURES & BENEFITS

- 100% Solids / Solvent free
- Exceptionally fast cure
- Convenient 1:1 mix ratio
- No corrosive by-products
- Environmentally friendly
- Low shrinkage
- Virtually no exotherm

APPLICATIONS

- High voltage insulation
- Outdoor junction boxes
- Buried or exposed electrical connections
- PCB assemblies
- Cable splicing units

AVAILABILITY

- 55-Gallon Drums
- 5-Gallon Pails
- 600 ml Side-by-side cartridges

STORAGE / SHELF LIFE

SI9100 may be stored in original, unopened containers at, or below, 75F for up to one (1) year.

DESCRIPTION

Star Technology FISil SI9100 is a clear, general-purpose, silicone based protective gel for electrical / electronic enclosures, junction boxes and terminal blocks. Extremely hydrophobic, FISil SI9100 provides an excellent water-tight seal in buried or outdoor applications.

TYPICAL PROPERTIES

Physical Property	Test Method	Performance Range
Appearance (mixed)	Visual	Clear liquid
Viscosity (Mixed)	Brookfield	850 —1000 cps
Specific Gravity		0.96—1.06
Worklife @ 25C		<15 minutes
Cure Time @ 25C		7 Days
Hardness	ASTM D 2240	45 Shore 00
Service Temperature		-40C to 205C (-40F to 400F)
Dielectric Constant	ASTM D150	2.10 @100 Hz 2.45 @100 kHz
Dissipation Factor	ASTM D 150	0.020 @100 Hz 0.0038 @100 kHz
Dielectric Strength	ASTM D149	450 v/mil

ADDITIONAL INFORMATION

- Refer to Technical Bulletins for additional mixing, curing and handling procedures.
- As with any platinum-catalyzed silicone gel, the cure may be inhibited. Always check compatibility. Refer to Technical Bulletin for information.
- Even when fully cured, silicone gels can be soft with a tacky surface; however, uncured liquid may indicate cure inhibition or improper mixing.
- Not recommended for surfaces that are to be painted.

To the best of our knowledge, the information provide herein is accurate. However, Star Technology, Inc. does not assume any liability for the accuracy or completeness of the information contained herein. Final determination of the suitability of any material is the sole responsibility of the user. The information contained herein is considered typical properties and is not intended to be used as specifications for our products. This information is offered solely to assist purchaser in selecting the appropriate products for purchaser's own testing. All materials may present unknown hazards and should be used with caution. Although certain hazards are described herein and in the Safety Data Sheet, we cannot guarantee that these are the only hazards that exist.