

STAR Technology

FORMULATING • INNOVATIVE • SOLUTIONS

ER3280

Two Part Epoxy Potting & Encapsulating Compound

DESCRIPTION

ER3280 is an easy to mix clear two-part room temperature cure epoxy potting and encapsulating compound. **ER3280** has a convenient mix ratio of 1:1 by volume and a low viscosity that delivers outstanding flow and leveling properties. **ER3280** will adhere to most metals, wood, Styrofoam, glass, most engineering plastics, and many surface treated polyolifins. Because of the slow gel time and simple mix ratio, **ER3280** lends itself to a variety of manual and automated dispense possibilities. Viscosity may be thixotroed for vertical and non-sag applications. This product may contain fillers that may settle over time. Product may need to be stirred before using. Customer must determine suitability of product before using.

Data contained herein are believed to be reliable. Fit-for-use testing should be conducted by each user.

TYPICAL PROPERTIES	TEST METHOD	VALUE
Gel Time [100 Gram Mass at 75 ° F] (minutes):	ASTM D2471	30
Shore D Hardness:	ASTM D2240	80
Lap Shear [CRS to CRS] (psi):	ASTM D1002	1600
Part A:		
Specific Gravity (g/cc):	ASTM D1475	1.16
Viscosity (cps):	ASTM D2393	12000
Color:		Clear
Part B:		
Specific Gravity (g/cc):	ASTM D1475	.96
Viscosity (cps):	ASTM D2393	4050
Color:		Clear
Mix Ratio:		
By Weight:		100:84
By Volume:		1:1

To the best of our knowledge, the information contained herein is accurate. However, STAR TECHNOLOGY, Inc., does not assume any liability whatsoever for the accuracy or completeness of the information contained herein. Final determination of the suitability of any material is the sole responsibility of the user. The information contained herein is considered typical properties and is not intended to be used as specifications for our products. This information is offered solely to assist purchaser in selecting the appropriate products for purchaser's own testing. All materials may present unknown hazards and should be used with caution. Although certain hazards are described herein and in the material safety data sheet, we cannot guarantee that these are the only hazards that exist. Repeated and prolonged exposure to epoxy resins can cause sensitization or other allergic responses.



STAR Technology

FORMULATING • INNOVATIVE • SOLUTIONS

ER3280

Two Part Epoxy Potting & Encapsulating Compound

APPLICATION PROCEDURES

Carefully weigh out appropriate amounts of resin and hardener into a clean mixing container and thoroughly mix until all streaks and striations are gone. Scrape the sides and bottom frequently to ensure complete mixing.

CAUTION: Unmixed compound from the sides or bottom of the container can cause soft spots or uncured areas in the completed piece. To prevent this, transfer the entire mixed contents to a second clean container and remix for a short time before using.

PRECAUTIONS

For industrial use only. Keep away from children.

Refer to the Material Safety Data Sheets (MSDS forms) pertaining to this product before using.

Avoid contact with skin or eyes. In the event of an eye splash or contact, immediately flush with cold water for 15 minutes and contact a physician. If skin contact occurs, wash with mild soap and water. The wearing of safety glasses with side shields and impervious gloves is recommended.

RESIN AND HARDENER WARNING STATEMENT

May cause allergic skin reaction. Avoid all contact with skin, eyes, and clothing. Wash thoroughly after handling.

To the best of our knowledge, the information contained herein is accurate. However, STAR TECHNOLOGY, Inc., does not assume any liability whatsoever for the accuracy or completeness of the information contained herein. Final determination of the suitability of any material is the sole responsibility of the user. The information contained herein is considered typical properties and is not intended to be used as specifications for our products. This information is offered solely to assist purchaser in selecting the appropriate products for purchaser's own testing. All materials may present unknown hazards and should be used with caution. Although certain hazards are described herein and in the material safety data sheet, we cannot guarantee that these are the only hazards that exist. Repeated and prolonged exposure to epoxy resins can cause sensitization or other allergic responses.