

FLEX-SEAL Extreme Flexible Epoxy Potting Compound

DESCRIPTION:

FLEX-SEAL Extreme is a room temperature cure NON-DOT-Hazardous flexible potting compound designed for shock sensitive components, and moisture proofing electronic assemblies and sub-assemblies. The low mixed viscosity of FLEX-SEAL Extreme make intimate wet out possible. FLEX-SEAL Extreme bonds easily to metal frames and lead wires.

PHYSICAL PROPERTIES:

Part A:	
Color:	Black
Viscosity (cps):	5,000
Specific Gravity (g/cc):	1.00
Part B:	
Color:	Clear
Viscosity (cps):	5,000
Specific Gravity (g/cc):	1.12
Mixed Viscosity (cps):	5,000
Cured Color:	Black
Mix Ratio by volume:	2:1
Gel Time [100g mass] (minutes):	20
Shore A Hardness:	35
Tensile (psi):	1300
Elongation (%):	500
Shrinkage (%):	0.8
Dielectric Strength (V/mil):	330
Weight Loss [150°C, 6 hours] (%):	<1
Service Temperature:	80°C

To the best of our knowledge, the information contained herein is accurate. However, STAR TECHNOLOGY, Inc., does not assume any liability whatsoever for the accuracy or completeness of the information contained herein. Final determination of the suitability of any material is the sole responsibility of the user. The information contained herein is considered typical properties and is not intended to be used as specifications for our products. This information is offered solely to assist purchaser in selecting the appropriate products for purchaser's own testing. All materials may present unknown hazards and should be used with caution. Although certain hazards are described herein and in the material safety data sheet, we cannot guarantee that these are the only hazards that exist. Repeated and prolonged exposure to epoxy resins can cause sensitization or other allergic responses.