

STAR Technology

FORMULATING • INNOVATIVE • SOLUTIONS

U-66-2

Two-Part Brush-On Epoxy

DESCRIPTION

U-66-2 is a two-part epoxy designed for use as an electrical general purpose brush-on compound ideal for general maintenance. U-66-2 is available in pre-measured kits of 1 pound, 2 pound, 100 grams and 50 grams. U-66-2 is also available in larger pail and drum kits. Material brushes on with ease and has a fast room temperature cure in thin films. The cured material shows excellent resistance to a variety of chemicals including; water, alkali, hydrocarbons, glycol ethers, ketones, detergents, and chlorinated hydrocarbon solvents. When mixed, U-66-2 will require no baking to achieve the ultimate curing properties. U-66-2 will cure tack free in 4 – 8 hours. U-66-2 will completely cure after baking for 5 minutes at 100° C.

U-66-2 is available in 50 gram burst packs, 100 gram burst packs, 1 # kits, 2# kits, 1 gallon pails, 5 gallon pails, and 55 gallon drums.

Data contained herein are believed to be reliable. Fit-for-use testing should be conducted by each user.

BENEFITS

Available in Pre-measured kits
Class H temperature use

Excellent Coverage
Excellent Chemical Resistance

TYPICAL PROPERTIES (cured 7 Days at 75 °F)

	<u>TEST METHOD</u>	<u>VALUE</u>
Pot Life [250 Gram Mass at 75 °F] (minutes):	ASTM D2471	25
Shore D Hardness:	ASTM D2240	80
Lap Shear [CRS to CRS] (psi):		
23 °C:	ASTM D1002	1,300
150 °C:	ASTM D1002	100
Tensile Strength (psi):	ASTM D638	6,000
Tensile Modulus (psi):		363,000
Elongation (%):		4.0
Flexural Strength (psi):	ASTM D790	15,000
Flexural Modulus (psi):		400,000
Tg (° C):	ASTM D3418	105
Weight Loss [28 days @ 188 °C] (%):		1.58
Water Absorption [28 days at 25 °C] (%):		0.64
Dissipation Factor:		
48 Hour Water Immersion:		9.87×10^{-3}
48 Hour 50% Relative Humidity:		9.57×10^{-3}
Dielectric Constant:		
48 Hour Water Immersion:		1.56
48 Hour 50% Relative Humidity:		1.61
Volume Resistivity (Ω cm):		
48 Hour Water Immersion:		9.63×10^{15}
48 Hour 50% Relative Humidity:		9.49×10^{15}

To the best of our knowledge, the information contained herein is accurate. However, STAR TECHNOLOGY, Inc., does not assume any liability whatsoever for the accuracy or completeness of the information contained herein. Final determination of the suitability of any material is the sole responsibility of the user. The information contained herein is considered typical properties and is not intended to be used as specifications for our products. This information is offered solely to assist purchaser in selecting the appropriate products for purchaser's own testing. All materials may present unknown hazards and should be used with caution. Although certain hazards are described herein and in the material safety data sheet, we cannot guarantee that these are the only hazards that exist. Repeated and prolonged exposure to epoxy resins can cause sensitization or other allergic responses.

STAR Technology

FORMULATING • INNOVATIVE • SOLUTIONS

U-66-2

Two-Part Brush-On Epoxy

Part A:			
	Specific Gravity (g/cc):	ASTM D1475	1.38
	Viscosity (cps):	ASTM D2393	Thixotropic Paste
	Color:		Brick Red
Part B:			
	Specific Gravity (g/cc):	ASTM D1475	1.02
	Viscosity (cps):	ASTM D2393	1,200
	Color:		Light Straw
Mixed Product:			
	Specific Gravity (g/cc):	ASTM D1475	1.33
	Viscosity (cps) (20 rpm):	ASTM D2393	33,000
	Color:		Brick Red
Mix Ratio:			
	By Weight:		100:17
Shelf Life (months):			12

APPLICATION PROCEDURES

Carefully weigh out appropriate amounts of resin and hardener into a clean mixing container and thoroughly mix until all streaks and striations are gone. Scrape the sides and bottom frequently to ensure complete mixing.

CAUTION: Unmixed compound from the sides or bottom of the container can cause soft spots or uncured areas in the completed piece. To prevent this, transfer the entire mixed contents to a second clean container and remix for a short time before using.

PRECAUTIONS

For industrial use only. Keep away from children. Refer to the Material Safety Data Sheets (MSDS forms) pertaining to this product before using. Avoid contact with skin or eyes. In the event of an eye splash or contact, immediately flush with cold water for 15 minutes and contact a physician. If skin contact occurs, wash with mild soap and water. The wearing of safety glasses with side shields and impervious gloves is recommended.

WARNING STATEMENT

May cause allergic skin reaction. Avoid all contact with skin, eyes, and clothing. Wash thoroughly after handling.