

610-04

Epoxy Laminating System

DESCRIPTION

STAR Technology 610-04 is a gray, filled laminating system for intermediate high temperature applications. 610-04 may used in applications up to 325°F and requires a heat cure for applications above 150°F. This system provides good cloth wet-out without drain off. It will initially cure at room temperature to allow de-molding. High temperature properties are obtained after post curing. This system can be operated continuously at 275°F or intermittently at 325°F. 610-04 has a pot life of around forty-five minutes. The overall size, thickness, and layup speed will influence the desirable pot life of laminating system. In general, larger laminates and bagging operations will call for a slow hardener. Typical applications for 610-04 include vacuum form molds, high temperature bonding fixtures, prototype injection molds, RIM molds, spray metal molds, and compression molds.

BENEFITS

Exceptional wet-out No vertical drain off

Excellent dimensional stability

Excellent intermediate high temperature properties

TYPICAL PROPERTIES	TEST METHOD	<u>VALUE</u>
Mix Ratio		
By Weight		100:14.6
By Volume		100:17.9
Mixed Viscosity (cps):	ASTM D2393	5,000
Density (lbs/cu in):	ASTM D1475	0.0451
(lbs/gal):		10.41
Pot Life at 75° F (minutes):	ASTM D2471	50
Color:		Grey
Cure Schedule:		
24 hours @ 75°F + 2 hours @ 150°F + 1 hour @ 200°F + 1 hour @ 250°F + 1 hour @ 300°F + 2 hours @ 350°F		
Shore Hardness (D):	ASTM D2240	87
Tensile Strength (psi):	ASTM D638	5,500
Flexural Strength (psi):	ASTM D790	11,000
Flexural Modulus (psi):	ASTM D790	549,000
Compressive Ultimate Strength (psi):	ASTM D695	13,900
Glass Transition Temperature (° F):		242
Maximum Service Temperature (° F):		325

To the best of our knowledge, the information contained herein is accurate. However, STAR TECHNOLOGY, Inc., does not assume any liability whatsoever for the accuracy or completeness of the information contained herein. Final determination of the suitability of any material is the sole responsibility of the user. The information contained herein is considered typical properties and is not intended to be used as specifications for our products. This information is offered solely to assist purchaser in selecting the appropriate products for purchaser's own testing. All materials may present unknown hazards and should be used with caution. Although certain hazards are described herein and in the material safety data sheet, we cannot guarantee that these are the only hazards that exist. Repeated and prolonged exposure to epoxy resins can cause sensitization or other allergic responses.



610-04

Epoxy Laminating System

APPLICATION PROCEDURE

Carefully weigh out appropriate amounts of resin and hardener into a clean container and mix until all streaks are gone. Scrape the sides and bottom frequently to ensure complete mixing.

NOTE: To obtain optimum service temperature follow the suggested curing schedule with thermocouple monitoring. Thermocouple monitoring is recommended on all post cured tools. High temperature tools must be post cured prior to use. High temperature tools should be cured 50°F beyond anticipated use temperature.

CAUTION: Unmixed material from the sides or bottom of the container can cause soft spots or uncured areas in the completed tool. To prevent this, transfer the entire mixed contents to a second clean container and re-mix for a short time before using.

Additional Cure Schedule - If thermocouple monitoring equipment is not available then a longer step cure is a better choice, e.g.

2 hours @ 150°F + 2 hours @ 200°F +2 hours @ 250°F + 2 hours @ 300°F +2 hours @ 350°F

SAFETY PRECAUTIONS

For industrial use only. Keep away from children.

Refer to the Safety Data Sheets (SDS forms) pertaining to this product before using.

Avoid contact with skin or eyes. In the event of an eye splash or contact, immediately flush with cold water for 15 minutes and contact a physician. If skin contact occurs, wash with mild soap and water. The wearing of safety glasses with side shields and impervious gloves is recommended.

RESIN WARNING STATEMENT

Warning! Causes irritation. May cause allergic skin reaction. Avoid all contact with skin, eyes, and clothing. Wash thoroughly after handling.

HARDENER WARNING STATEMENT

Danger! Corrosive. Causes burns to eye and skin. May cause allergic skin and/or respiratory reaction or sensitization. Do not get in eyes, on skin or clothing. Keep container closed. Use with adequate ventilation. Wash thoroughly after handling.

To the best of our knowledge, the information contained herein is accurate. However, STAR TECHNOLOGY, Inc., does not assume any liability whatsoever for the accuracy or completeness of the information contained herein. Final determination of the suitability of any material is the sole responsibility of the user. The information contained herein is considered typical properties and is not intended to be used as specifications for our products. This information is offered solely to assist purchaser in selecting the appropriate products for purchaser's own testing. All materials may present unknown hazards and should be used with caution. Although certain hazards are described herein and in the material safety data sheet, we cannot guarantee that these are the only hazards that exist. Repeated and prolonged exposure to epoxy resins can cause sensitization or other allergic responses.